



Professional Products  
Professional Results



# 6100

## Mold Resistant Coating\* CLEAR

- Permeable coating allows substrate to breathe
- Tested by independent laboratories

\*Resists mold growth on the dry coating surface.

NET CONTENTS: 5 Gallons

For Professional Use Only

Calculated VOC: 90 g/l

**FIBERLOCK IAQ 6100 NO. 8361 CLEAR  
WARNING | ATTENTION**



H319 - Causes serious eye irritation.  
H317 - May cause an allergic skin reaction.  
H351 - Suspected of causing cancer.  
H411 - Toxic to aquatic life with long lasting effects.

Obtain special instructions before use.; Wear protective gloves/ protective clothing/eye protection/face protection.; Use personal protective equipment as required.; Avoid breathing mist/ vapours/spray.; Avoid release to the environment.; Contaminated work clothing should not be allowed out of the workplace.; See SDS for full list of P phrases

IF exposed or concerned: Get medical advice/attention.; Specific treatment (see advice on this label).; Wash contaminated clothing before reuse.; IF ON SKIN: Wash with plenty of soap and water.; IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.; If skin irritation or rash occurs: Get medical advice/attention.; See SDS for full list of P phrases

**Canadian Contact Info:**  
**4050-B Sladeview Crescent Suite 200**  
**Mississauga, ON L5L 5Y5 Canada**

**CAUTION!**  
**KEEP OUT OF REACH OF CHILDREN.**

Do not take internally. Close container after each use.  
Keep from freezing.  
Store between 40°F (4.5°C) and 90°F. (32°C)  
24 hour Emergency "CHEM-TEL" - 1-800-255-3924

H319 - Provoque une sévère irritation des yeux.  
H317 - Peut provoquer une allergie cutanée.  
H351 - Susceptible de provoquer le cancer .  
H411 - Toxique pour les organismes aquatiques, entraîne des effets néfastes à long terme.

Se procurer les instructions avant utilisation.|Porter des gants de protection/des vêtements de protection/un équipement de protection des yeux/du visage.|Utiliser l'équipement de protection individuel requis.|Éviter de respirer les brouillards/vapeurs/aérosols.|Éviter le rejet dans l'environnement.|Les vêtements de travail contaminés ne devraient pas sortir du lieu de travail.|Voir SDS pour la liste complète des phrases P

EN CAS d'exposition prouvée ou suspectée: Consulter un médecin.|Traitement spécifique (voir les conseils sur cette étiquette).|Laver les vêtements contaminés avant réutilisation.|EN CAS DE CONTACT AVEC LA PEAU: laver abondamment à l'eau et au savon.|EN CAS DE CONTACT AVEC LES YEUX: rincer avec précaution à l'eau pendant plusieurs minutes. Enlever les lentilles de contact si la victime en porte et si elles peuvent être facilement enlevées. Continuer à rincer.|En cas d'irritation ou d'éruption cutanée: consulter un médecin.|Voir SDS pour la liste complète des phrases P

For Technical Information call 800.342.3755

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use of this product are beyond our control. Neither ICP Construction, Inc., nor its agents shall be responsible for the use of this product or any procedures or apparatus mentioned. We recommend that the prospective user determine the suitability of, for each specific project and for the health and safety of personnel working in the area.

For additional information check Safety Data Sheet (SDS) or Product Data Sheet (PDS) available online at [www.fiberlock.com](http://www.fiberlock.com).

IAQ, the IAQ Logo and other marks on this label are trademarks of ICP Construction, Inc.

# 8361-5 Clear



150 Dascomb Rd.  
Andover, MA 01810  
(800) 342-3755  
[www.fiberlock.com](http://www.fiberlock.com)  
Rev. 04.25.18

IAQ 6100 is a clear mold resistant coating for professional use, that contains a fungistatic agent to resist mold growth on the dry coating surface. IAQ 6100 is a durable, flexible, and permeable 100% acrylic water-based coating. IAQ 6100 has been tested by independent and certified laboratories to prove resistance to mold growth on the surface of the coating, and has successfully passed both ASTM G-21 and ASTM D-3273 mold resistance testing with the highest scores possible. IAQ 6100 is recommended for use on wood, plaster, wallboard, sheetrock, concrete, masonry block, primed metal and galvanized metal. IAQ 6100 can also be used on new structural materials during building construction.

### SURFACE PREPARATION

Warning! If you scrape, sand, or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

Surfaces to be coated must be free of dust, mildew, mold, dirt, grease, loose paint, oil, glue size, calcimine, wax, soap and other surface contamination. Clean mold stained surfaces with IAQ Advanced Peroxide Cleaner, or use an EPA registered antimicrobial disinfectant cleaner such as IAQ 2000, IAQ 2500, ShockWave or ShockWave RTU.

Patch irregularities with vinyl patching paste or an appropriate patching compound. IAQ 6100 is self-priming over bare sheetrock, composition board, ceiling tile and concrete.

WALLBOARD, SHEETROCK, GYPSUM BOARD - Joint cement should be sanded smooth, but avoid abrading the paper.

FERROUS METAL - Clean, then prime with IAQ 4000 rust inhibiting direct-to-metal primer.

WOOD - Seal knots and stains with IAQ 5000 stain-blocking primer.

MASONRY BLOCK - Apply one coat of IAQ 3000 block filler if a denser surface is desired.

### APPLICATION TOOLS

Apply IAQ 6100 with brush, roller or airless spray equipment.

- Brush: Synthetic, nylon or polyester bristle
- Roller: Synthetic fiber 3/8" nap or longer
- Spray: .015 to .019 tip @ 2000-2800 P.S.I.

### PRODUCT APPLICATION

IAQ 6100 is supplied ready to use, but can be thinned sparingly with water (up to 1/2 pint water per gallon) for proper application consistency if necessary. Apply IAQ 6100 generously and uniformly by brush, roller, or airless spray.

Apply one coat of IAQ 6100 and ensure that the finished surface is properly sealed. To ensure that the finished surface is properly sealed, two-coats may be required on some porous surfaces.

### COVERAGE

- Smooth Surfaces: 350-600 ft<sup>2</sup>/gal.
- Porous Surfaces: 250-300 ft<sup>2</sup>/gal.

### DRYING TIME @ 70°F 50% R.H

- To Touch: 1 Hour
- Recoat: 4-8 Hours

### CLEANUP

Clean tools and drippings with warm soapy water before IAQ 6100 dries. The coating and any contaminated diking material should be thoroughly air dried and collected into drums. The drums should be sealed and labeled and land-filled or incinerated according to local, regional and national regulations.

### PRECAUTIONS

Store in a dry place at temperatures between 40°F (4.5°C) and 90°F. (32°C). Keep closures tight and containers upright to prevent leakage. Product is non-combustible. Stir thoroughly. Do not mix with any other coatings, solvents or colors in oil. The IAQ 6100 coating is resistant to mold only on the surface of the coating. No mold resistance claim is made other than to the coating itself. The use of this product does not protect users or others against food-borne or disease-causing bacteria, viruses, germs or other disease-causing organisms. Do not apply when air or surface temperature is below 50°F, or when drying conditions are poor or when surfaces are above a 15% moisture level content. Use adequate ventilation during application. When applying with a sprayer, wear a NIOSH approved respirator with any R, P, N or HE filter. For interior use only.