



VIPER CONCRETE & STONE DENSIFIER

Lithium Based Concrete & Stone Densifier

X Grout X Concrete ✓ Stone X Saltillo

X = Primary Use ✓ = Secondary Use



HYDRO-FORCE™

One U.S. Gallon (3.79 Litres)

- Easy to apply.
- Penetrates, and cures quickly, usually within an hour.
- Reduces dusting and wear by hardening surface.
- Simplifies maintenance by reducing need for topical coating.
- Makes the surface less permeable to liquids so less sealer is needed.
- Increases surface density so you can achieve a higher gloss after polishing.

DIRECTIONS

Pretesting:

Floor temperature should be above 50 degrees F and below 100 degrees F for several hours before and after application. Outside application should be done when it will not rain for several hours. Check the absorbency of each slab before proceeding. Spray section with water to determine how absorbent the concrete is and if absorbency is consistent. This will also help you determine the coverage that should be expected. Wax or urethane or other topical coatings need to be thoroughly stripped before application.

Cleaning

Surface needs to be structurally intact and thoroughly cleaned before application. Do not use pine or d'limonene-based cleaners without additional rinsing. The use of a rotary agitation surface cleaner such as a Hydro-Force SX15 qualifies as additional rinsing. Application can start as soon as surfaces are dry. Air movers can be used to shorten drying time.

Application

Protect surrounding surfaces from overspray and splashing of the product.

Apply undiluted with low pressure sprayer. Do not aerosolize the product. Apply enough product to wet the surface without forming puddles. Spread evenly with soft synthetic brush. Surface should look dry in 5 to 10 minutes. Any areas that dry prematurely should be sprayed again. Allow treated surfaces to dry before any additional procedures are initiated. After drying, remove any powdered residue using a stiff brush before continuing. At this point the floor can be polished and/or sealed. Polishing time will be reduced and the surface will absorb less sealer. Adjust procedures and/or applications appropriately.

Shipment and Storage

Do not allow product to freeze. It is not freeze thaw stable. Store in a cool dry place with container sealed when not in use.

CONTAINS

Deionized water (CAS# 7732-18-5), Lithium Silicate (CAS# 12627-14-4).

IMPORTANT NOTICE TO PURCHASER: Seller's and manufacturer's liability for any and all losses or damages resulting from any cause whatsoever shall in no event exceed the purchase price of this product, with respect to which losses or damages are claimed. Before using, the user shall determine the suitability of this product for its intended use, and user assumes all risk and liability whatsoever in connection therewith. Go to www.hydroforce.com/sds for additional safety, regulatory and liability information.

WARNING!



Keep out of reach of children.

HAZARD STATEMENTS:

Causes skin irritation. Causes eye irritation. Harmful if inhaled.

PRECAUTIONARY STATEMENTS:

Do not breathe dust/fume/gas/mist/vapors/spray. Do not get in eyes, on skin, or on clothing. Wear protective gloves/protective clothing/eye protection/face protection.

ADVERTENCIA!



Mantener fuera del alcance de los niños.

INDICACIONES DE PELIGRO:

Causa irritación a la piel. Causa irritación al ojo. Dañoso si inhalado.

DECLARACIONES DE PRECAUCIÓN:

No respirar polvo, humo, gas, neblina, vapores, rociador. Evitar el contacto a los ojos, en la piel o en la ropa. Usar guantes, ropa, lentes y mascarillas de protección.

VIPER CONCRETE & STONE DENSIFIER



May cause skin and eye irritation. Avoid contact with skin and eyes. In case of contact, immediately flush with plenty of water, seek medical advice if irritation persists.

Susceptible d'irriter la peau et les yeux. Évitez tout contact avec la peau et les yeux. S'il y a contact, lavez-vous immédiatement à la grande eau. Consultez un médecin si l'irritation se fait persistante.

SEE SAFETY DATA SHEET
VOIR LA FICHE SIGNATÉTIQUE

See Safety Data Sheet (SDS):
www.hydroforce.com/sds
for additional safety and regulatory information.

Another fine product from Hydro-Force Manufacturing
4282 South 590 West, Salt Lake City, UT 84123
www.hydroforce.com

FLAMMABILITY



CH50GL

RTU ph - 11.0